

Sponsor: Martin Werneholm Airinum AB c/o Ahouse Östermalmsgatan 26A Stockholm, 11426 SWEDEN

Latex Particle Challenge Final Report

Test Article:	Air Filter Opti	
Purchase Order:	AIR0003	
Study Number:	1504430-S01	
Study Received Date:	04 Apr 2022	
Test Started Date:	25 Apr 2022	
Test Finished Date:	26 Apr 2022	
Testing Facility:	Nelson Laboratories, LLC	
	6280 S. Redwood Rd.	
	Salt Lake City, UT 84123 U.S.A.	
Test Procedure(s):	Standard Test Protocol (STP) Number:	STP0005 Rev 08
Deviation(s):	None	

Summary: This procedure was performed to evaluate the non-viable particle filtration efficiency (PFE) of the test article. Monodispersed polystyrene latex spheres (PSL) were nebulized (atomized), dried, and passed through the test article. The particles that passed through the test article were enumerated using a laser particle counter.

A one-minute count was performed, with the test article in the system. A one-minute control count was performed, without a test article in the system, before and after each test article. Control counts were performed to determine the average number of particles delivered to the test article. The filtration efficiency was calculated using the number of particles penetrating the test article compared to the average of the control values. During testing and controls, the air flow rate is maintained at 1 cubic foot per minute (CFM) \pm 5%.

The procedure employed the basic particle filtration method described in ASTM F2299, with some exceptions; notably the procedure incorporated a non-neutralized challenge. In real use, particles carry a charge, thus this challenge represents a more natural state. The non-neutralized aerosol is also specified in the FDA guidance document on surgical face masks. All test method acceptance criteria were met. Testing was performed in compliance with US FDA good manufacturing practice (GMP) regulations 21 CFR Parts 210, 211 and 820.

Test Side:Black SideArea Tested:91.5 cm²Particle Size:0.3 μmLaboratory Conditions:20.1°C, 22% relative humidity (RH) at 1244; 20.4°C, 22% RH at
1328Average Filtration Efficiency:>99.9971%Standard Deviation:0.00017



Lisa Bonner electronically approved for Study Director

Curtis Gerow

28 Apr 2022 17:56 (+00:00) Study Completion Date and Time

brd

FRT0005-0001 Rev 7 Page 1 of 2



Results:

Test Article Number	Test Article Counts	Average Control Counts	Filtration Efficiency (%)
1	<1 ^a	11,290	>99.9970
2	<1 ^a	10,940	>99.9970
3	<1 ^a	11,063	>99.9970
4	<1 ^a	11,881	>99.9972
5	<1 ^a	12,606	>99.9974

^a There were no detected particles penetrating this filter during testing.