

Sponsor: Martin Werneholm Airinum AB c/o Ahouse Östermalmsgatan 26A Stockholm, 11426 SWEDEN

Bacterial Filtration Efficiency (BFE) Final Report

Test Article:	Air Filter Opti	
Purchase Order:	AIR0003	
Study Number:	1504431-S02	
Study Received Date:	04 Apr 2022	
Test Started Date:	20 Apr 2022	
Test Finished Date:	26 Apr 2022	
Testing Facility:	Nelson Laboratories, LLC	
	6280 S. Redwood Rd.	
	Salt Lake City, UT 84123 U.S.A.	
Test Procedure(s):	Standard Test Protocol (STP) Number:	STP0004 Rev 19
Deviation(s):	None	

Summary: The BFE test is performed to determine the filtration efficiency of test articles by comparing the bacterial control counts upstream of the test article to the bacterial counts downstream. A suspension of *Staphylococcus aureus* was aerosolized using a nebulizer and delivered to the test article at a constant flow rate and fixed air pressure. The challenge delivery was maintained at $1.7 - 3.0 \times 10^3$ colony forming units (CFU) with a mean particle size (MPS) of $3.0 \pm 0.3 \mu m$. The aerosols were drawn through a six-stage, viable particle, Andersen sampler for collection. This test method complies with ASTM F2101-19 and EN 14683:2019+AC:2019, Annex B.

All test method acceptance criteria were met. Testing was performed in compliance with US FDA good manufacturing practice (GMP) regulations 21 CFR Parts 210, 211 and 820.

Test Side:	Black Side
BFE Test Area:	~7.8 cm ²
BFE Flow Rate:	28.3 Liters per minute (L/min)
Conditioning Parameters:	85 \pm 5% relative humidity (RH) and 21 \pm 5°C for a minimum of 4 hours
Positive Control Average:	2.1 x 10 ³ CFU
Negative Monitor Count:	<1 CFU
MPS:	3.0 µm



James Luskin electronically approved

Study Director

James Luskin

29 Apr 2022 15:16 (+00:00) Study Completion Date and Time

tml



Results:

Air Filter Opti:

Test Article Number	Percent BFE (%)
1	>99.9 ^a
2	>99.9
3	>99.9 ^a
4	>99.9
5	>99.9 ^a

^a There were no detected colonies on any of the Andersen sampler plates for this test article.

The filtration efficiency percentages were calculated using the following equation:

$$C - T$$
 C = Positive control average

ge $\% BFE = \frac{C-T}{C} x \ 100$ T = Plate count total recovered downstream of the test article Note: The plate count total is available upon request